

SPRAYROQ SPRAYWALL

**SUPERIOR STRENGTH,
SUPERIOR PROTECTION.**

Providing structural integrity
with infiltration control & chemical
resistance for concrete,
steel, masonry, fiberglass,
& a multitude of other
surfaces.



SPRAYROQ
STRUCTURAL PROTECTIVE LINING SYSTEMS

SprayWall provides both corrosion and abrasion resistance that can be applied at any desired thickness. With one of the quickest curing times in the industry, it allows your newly protected structure to be returned to service immediately after the application is complete. Uses include:

- Manholes
- Lift Stations
- Wet Wells
- Tanks
- Grit Chambers
- Clarifiers
- Digestors
- Box Culverts
- Pipelines (man entry only)
- Tunnels
- Secondary Containment
- Lagoons

Description:	Method:	Imperial:	Metric:
• Flexural Modulus	• ASTM D790	• 735,000 psi*	• 5,067.6 MPa*
• Long Term Flexural Modulus	• ASTM D2990	• 529,000 psi*	• 3,647.3 Mpa*
• Flexural Strength	• ASTM D790	• 14,000 psi*	• 96.5 MPa*
• Compressive Strength	• ASTM D695	• 18,000 psi*	• 54.5 MPa*
• Tensile Strength	• ASTM D638	• 7,450 psi*	• 51.4 MPa*
• Tensile Modulus	• ASTM D638	• 425,000 psi*	• 2,930.3 MPa*
• Elongation	• ASTM D638	• 4% at break*	• 4% at break*
• Abrasion (Taber CS17)	• ASTM D4060	• 17.7 mg loss*	• 17.7 mg loss*
• Hardness, Shore D	• ASTM D2240	• 90**	• 90**
• Density	• -	• 87 lbs/cf	• 1,394 Kg/m3**
• Adhesion to Concrete	• ASTM D4541	• Substrate Failure**	• Substrate Failure**

* Texas Research Institute, Austin, TX
 ** Sprayroq Inc. Laboratory

Cure & Recoat Faster than Ever:

After the A and B components are mixed, SprayWall begins to gel in about 8 seconds with a tack free condition after two minutes. Within 30 minutes**, the initial cure is completed and the structure is capable of accepting flow while the complete curing continues for the next 4-6 hours.

** Initial cure may take longer as environmental conditions and application thickness must be taken into account. Coating should always be cooled to ambient temperature before a return to service.

CONTACT US TO LEARN MORE!

(205) 957-0020
 INFO@SPRAYROQ.COM

2870 Crestwood Blvd
 Irondale, AL 35210

